

10/615,150

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	0	("2367715").URPN.	USPAT	OR	OFF	2005/10/18 19:16
L2	1756	(219/645,653,612,635,659).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2005/10/18 19:17
L3	3363	(156/380.2,500,272.2,272.6).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2005/10/18 19:17
L4	5525	(428/457).CCLS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2005/10/18 19:17
L5	10609	L2 or L3 or L4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17
L6	172238	(bond\$3 or laminat\$3 or weld\$3) and convey\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17
L7	22115	L6 and (metal with (bond\$3 or laminat\$3 or weld\$3) with metal)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17
L8	22115	L7 and convey\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17
L9	1028	L8 and (induct\$3 with heat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17
L10	398	L9 and (metal with (sheet or layer) with (bond\$3 or laminat\$3 or weld\$3) with metal with (sheet or layer))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:17

L11	35	L5 and L10	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:18
L12	215	10 and (metal with bond\$3 with metal)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:19
L13	198	12 and (induction with heat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:24
L14	198	13 and (convey\$3 or roller\$1)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:24
L15	2	14 and (metal with treat\$4 with fabricat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:22
L16	4	9 and (metal with treat\$4 with fabricat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:24
L17	137	9 and (metal with fabricat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:23
L18	31	14 and (metal with fabricat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:23
L19	137	17 and convey\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:23
L20	120	17 and (induction with heat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:24

L21	120	20 and (convey\$3 or roller\$1)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:25
L22	4	21 and (metal with treat\$4 with fabricat\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/10/18 19:24